



PARAMOUNT®
DUAL PURPOSE FLOOR FINISH

Z29

TECHNICAL DATA SHEET

GENERAL INFORMATION

PARAMOUNT has been formulated to meet the need of a floor finish which can be used in both regular and ultra high speed floor maintenance programs. PARAMOUNT is easy to apply and maintain while providing excellent gloss and wear. Recommended for use on vinyl asbestos, vinyl, reinforced vinyl, asphalt, and other types of resilient floors.

DIRECTIONS

1. Completely strip off all old floor finish using a Cello heavy duty floor stripper.
2. Remove all traces of stripper and old finish. Rinse floor 2 or 3 times with cool clean water. Allow floor to dry completely before coating the surface.
3. Pour PARAMOUNT into a clean mop bucket. Use a clean synthetic string mop free of all sizing. Saturate mop with floor finish and wring out until mop is damp, but not dripping.
4. Apply thin coats of PARAMOUNT until desired initial gloss is reached.
NOTE: Since no two floors are the same, the number of coats applied will vary. To avoid streaking, hazing, or re-emulsification of the previous coat, allow appropriate drying time. Wait until the finish is dry to the touch, then wait an additional 15 minutes before application of the next coat.

MAINTENANCE

1. Dust mop daily, using an untreated dust mop, to remove loose soil and grit.
 2. To remove soil from the surface, mop or auto scrub with Cello's BEST YET! or TS LOW FOAM.
 3. Spray buff with Cello's REDEEM, HI-PRODUCTION, or HI-BEAM to restore the gloss, or burnish as needed.
 4. The occasional use of rejuvenators like SILVER STREAK, DRESS UP, or HI-BEAM will enhance the appearance of the floor.
 5. Machine scrub traffic lanes and heavily soiled areas when needed using TS LOW FOAM or BEST YET! Neutral Cleaner.
- Rinse and re-apply thin coats of PARAMOUNT as needed.

CAUTION: Keep out of reach of children.

SPECIFICATIONS

APPEARANCE: White opaque liquid

NONVOLATILE SOLIDS: 22.5±0.5

pH: 8.4±0.2

SPECIFIC GRAVITY: 1.03

COLOR ON FLOOR: Clear, nondiscoloring

GLOSS RETENTION: Excellent

GLOSS: Very Good

SCUFF RESISTANCE: Excellent

BLACK HEEL MARK RESISTANCE: Excellent

DETERGENT RESISTANCE: Excellent

WATER SPOT RESISTANCE: Outstanding

DRYING TIME: See note above

LEVELING: Excellent

SPRAY BUFFABILITY: Excellent

COVERAGE:

FIRST COAT: 1500 ± 500 sq. ft. per gallon depending upon porosity of the floor

SUBSEQUENT COATS: 2000-3000 sq. Ft.

KEEP FROM FREEZING

**Cello Professional
Products**

1354 Old Post Road
Havre de Grace, MD 21078
Toll Free: 800-638-4850
www.cello-online.com



CLASSIFIED BY
UNDERWRITERS LABORATORIES INC.®
AS TO SLIP RESISTANCE ONLY. 160S.

Z29 0205