



TECHNICAL DATA SHEET

GENERAL INFORMATION

HTF 25 HIGH TRAFFIC FINISH has been specifically formulated for high initial gloss and "wet look" response to burnishing. Due to its high solids HTF 25 will create this appearance with less coats than other floor finishes used. With HTF 25's outstanding durability to high traffic conditions, it is the recommended finish for retail stores (to include supermarkets, department stores, shopping malls), airports and schools.

HTF 25 is easily maintained with less effort due to its ability to repel heel marks and soil. Its tough film does not allow dirt penetration, yet will respond to daily burnishing for that "wet-look" appearance.

Recommended for use on vinyl asbestos, vinyl, reinforced vinyl, asphalt and other types of resilient floors as well as non-resilient terrazzo floors.

DIRECTIONS

1. Completely strip off all old floor finish using a Cello heavy duty stripper.
2. Remove all traces of stripper and old finish. Rinse floor 2 to 3 times with cool clear water. Use of Cello FLOOR CARE NEUTRALIZER in any one rinse will assure more complete removal of alkaline residue left from the stripping operation. Allow floor to dry completely before coating the surface.
3. Line the mop bucket with a trash liner to avoid contamination of the floor finish. Pour HTF 25 into mop bucket. Use a clean finish mop free of all sizing. Saturate mop with floor finish and wring out until mop is damp, but not dripping.
4. Apply thin to medium coats of HTF 25 until desired gloss is reached. Since no two floors are the same, the number of coats applied will vary.
NOTE: To avoid streaking, hazing, or re-emulsification of the previous coat, allow appropriate drying time. Wait until the finish is dry to the touch, then wait an additional 15 minutes before application of the next coat.
5. For optimum results burnish first coat using a white or other non-aggressive floor pad.

MAINTENANCE

1. Dust mop daily, using an untreated dust mop, to remove loose soil and grit.
2. To remove soil from the surface, mop or auto scrub with Cello's BEST YET!, LOW FOAM or NEUTRA GREEN.
3. Spray buff with Cello's ABOUT FACE, HI-PRODUCTION, or HI-BEAM to restore the gloss, or burnish as needed.
4. The occasional use of rejuvenators like Cello's SILVER STREAK, DRESS UP or HI-BEAM will enhance the appearance of the floor.
5. Machine scrub traffic lanes and heavily soiled areas when needed using Cello's BEST YET!, LOW FOAM or NEUTRA GREEN. Rinse and re-apply thin coats of HTF 25 as needed.

CAUTION: KEEP OUT OF REACH OF CHILDREN

SPECIFICATIONS

APPEARANCE: White emulsion

FRAGRANCE: Acrylic

NONVOLATILE SOLIDS: 25.5 ± .5

pH: 8.4 ± 0.2

SPECIFIC GRAVITY: 1.03

REPAIR ABILITY: Excellent

DRYING TIME: See note above

LEVELING: Excellent

DETERGENT RESISTANCE: Excellent

SCUFF RESISTANCE: Excellent

SCRATCH RESISTANCE: Excellent

WATER SPOT RESISTANCE: Excellent

COVERAGE:

FIRST COAT: 1500 ± 500 sq. ft. per gallon depending upon porosity of the floor

SUBSEQUENT COATS: 2000-3000 sq. ft. per gallon

KEEP FROM FREEZING

**Cello Professional
Products**

1354 Old Post Road
Havre de Grace, MD 21078
Toll Free: 800-638-4850
www.cello-online.com

Z35 20110216